



The Secret Architecture of Fungal Fibres: How *Ganoderma* Hyphae Control Composite Strength

*Sandeep. J, Ashwini. M, Shreya. S and Kushan. A

Department of Microbiology, College of Agriculture, Dharwad, University of Agricultural Sciences, Dharwad, Karnataka

*Corresponding Author's email: sandeepjavaprakash2003@gmail.com

Mycelium-based composites are often described simply as “fungus-bound” materials, but their mechanical behaviour is actually governed by a microscopic architecture of branching hyphae. In *Ganoderma*, this architecture can function as a natural reinforcing and binding network that interlocks lignocellulosic particles, transfers stress and influences porosity. Members of *Ganoderma* can possess a trimitic hyphal system, containing generative, skeletal and binding hyphae, providing multiple structural roles within the fungal network. Studies comparing fungal species and substrates show that hyphal morphology, network density, substrate structure, moisture and processing conditions can substantially alter composite strength. This makes *Ganoderma* particularly interesting not merely as a biological binder, but as a living microstructural engineer whose fibre architecture can potentially be controlled to design stronger and more functional sustainable composites.

Keywords: *Ganoderma*, fungal fibres, hyphae, mycelium composites, trimitic hyphae, mechanical strength, bio-composites, lignocellulose

Introduction: Strength Begins with a Hidden Network

A mycelium composite may look like a simple block of agricultural or wood waste, yet its strength originates from an invisible three-dimensional network. During growth, fungal hyphae penetrate pores, surround particles and create numerous contact points between otherwise disconnected substrate components. The resulting network acts as a biological binder and reinforcement system. For *Ganoderma*, this phenomenon becomes particularly interesting because its hyphal organization can include different specialized hyphal forms. Rather than behaving like a conventional synthetic adhesive, the fungal network develops through biological growth, branching and interconnection. Consequently, the final mechanical properties depend not only on the substrate but also on **how the fungus constructs its microscopic architecture.**

The Three-Fibre Secret of *Ganoderma*

The key to understanding *Ganoderma* composites lies in the **trimitic hyphal system.**

It can contain:

- **Generative hyphae** – relatively thin and actively growing structures that contribute to network formation.
- **Skeletal hyphae** – thicker, elongated structures that provide structural support.
- **Binding hyphae** – thick-walled and highly branched structures that help lock particles together.

Trimitic networks therefore combine flexibility, reinforcement and binding within the same biological material. Reviews of mycelium composites associate these thicker structural and binding hyphae with increased stiffness and mechanical integrity.

The important concept: *Ganoderma* does not simply “fill” the gaps between substrate particles—it builds a **hierarchical fibre network around them.**

How Hyphae Actually Strengthen the Composite

Mechanical interlocking

As hyphae grow around and between lignocellulosic particles, they create physical bridges. These bridges restrict particle movement when the composite is loaded.

This mechanism can be viewed as:

Particle → Hyphal bridge → Particle → Hyphal network → Particle

The greater the connectivity of this network, the more efficiently stresses can potentially be distributed throughout the composite.

Interfacial adhesion

Fungal cell walls contain structural components including **chitin and β -glucans**, together with proteins and other compounds. These components contribute to the integrity of individual hyphae and their interaction with the surrounding matrix.

Thus, strength is not produced by the hypha alone. It emerges from the **hypha–substrate interface**.

Stress redistribution

A dense fungal network can distribute locally applied forces across numerous interconnected paths. Instead of one substrate particle carrying the entire load, neighbouring particles can participate through the fungal network.

This is one reason why the **topology, branching and density** of mycelium are important structural variables.

Density: The Hidden Strength Dial

One of the simplest but most powerful relationships in mycelium composites is the connection between **density and mechanical performance**. Increasing density can reduce large pores and increase the amount of material available to carry load. Reviews have therefore reported a general relationship between increasing composite density and higher modulus or strength, although mycelium systems are more complex than conventional cellular materials.

For *Ganoderma*, density is influenced by:

hyphal growth + substrate particle size + substrate composition + moisture + compaction + drying

Therefore, a stronger composite is not necessarily obtained simply by growing “more fungus.” The **spatial arrangement of fungal biomass** matters.

The Substrate Changes the Fungal Architecture

Ganoderma does not build its network in an empty space. It grows through a substrate such as sawdust, agricultural residues or other lignocellulosic materials.

Consequently:

Substrate structure → fungal colonization → hyphal architecture → composite microstructure → mechanical behaviour

Experimental work with *G. fornicatum* and *G. williamsianum* demonstrated that both fungal species and lignocellulosic substrate type influence density and mechanical properties. Sawdust-based composites, for example, showed substantially different mechanical behaviour from rice-straw and corn-husk systems.

This reveals an important design principle:

The fungus and the substrate should be engineered as one system, rather than treated as independent components.


Why *Ganoderma* Is Mechanically Interesting

Recent experimental comparisons demonstrate that fungal species can produce noticeably different composite properties even when similar manufacturing approaches are used. In a 2026 study comparing fungal species, *Ganoderma* sp. composites displayed measurable tensile, compression and flexural performance, highlighting the influence of species-specific fungal architecture on material behaviour.

However, species alone cannot explain all performance differences. Substrate chemistry, density, growth conditions and post-processing can substantially modify the final structure. Current research increasingly treats mycelium composites through a **process–structure–property relationship**, rather than assuming that fungal identity alone determines strength.

The Microscopic Architecture–Macroscopic Strength Connection

The entire concept can be simplified into one structural chain:



This is the hidden architecture behind fungal composites.

The fascinating part is that a biological organism is simultaneously functioning as a **binder, reinforcement network and microstructural architect**.

Can We Engineer the Hyphal Network?

This is where *Ganoderma* composites become particularly exciting.

Future manufacturing could potentially control mechanical performance by manipulating:

- fungal strain selection,
- substrate particle size,
- substrate composition,
- moisture availability,
- growth temperature,
- colonization time,
- mycelial density,
- compression,
- drying and heat treatment.

Post-growth processing is especially important because densification and pressing can substantially modify the final mechanical structure of mycelium composites.

The future goal is therefore not simply:

“Grow fungus on waste.”

It is:

“Program fungal growth to construct a desired material architecture.”

The Biggest Knowledge Gap

Although microscopic imaging has revealed extensive hyphal networks, a major challenge remains: translating complex biological structures into **predictable engineering parameters**. Terms such as “dense mycelium” or “strong fungal network” are not sufficient for industrial material design.

Future studies should quantify:

hyphal diameter + branching density + network connectivity + hyphal orientation + pore size + interfacial adhesion + composite density

and connect these measurements directly to tensile, compression, flexural and impact properties.

Recent research is moving toward precisely this structure–property framework, including quantitative characterization of fungal matrices and their relationship with composite performance.

Conclusion

The strength of a *Ganoderma*-based composite is hidden in an architecture that cannot be seen from the outside. Its hyphae form interconnected biological fibres that penetrate, wrap and bind lignocellulosic particles. The combination of generative, skeletal and binding hyphae in trimitic systems provides a particularly interesting structural platform for developing mechanically functional biomaterials. Ultimately, **fungal composite strength is an architectural property as much as a chemical one**. Understanding and controlling hyphal diameter, branching, density, connectivity and substrate interaction could transform *Ganoderma* from a naturally occurring decomposer into a precisely engineered biological material-building system.

References

1. Appels, F. V. W., Camere, S., Montalti, E., Karana, E., Jansen, K. M. B., Dijksterhuis, J., Krijgheld, P., & Wösten, H. A. B. (2019). Fabrication factors influencing mechanical, moisture- and water-related properties of mycelium-based composites. *Materials & Design*, 161, 64–71.
2. Haneef, M., Ceseracciu, L., Canale, C., Bayer, I. S., Heredia-Guerrero, J. A., & Athanassiou, A. (2017). Advanced materials from fungal mycelium: Fabrication and tuning of physical properties. *Scientific Reports*, 7, 41292.
3. Yang, L., Park, D., & Qin, Z. (2021). Material function of mycelium-based bio-composite: A review. *Frontiers in Materials*, 8, 737377.
4. Attias, N., Danai, O., Tarazi, E., Pereman, I., & Grobman, Y. J. (2020). Implementing bio-design tools to develop mycelium-based products. *The Design Journal*, 23(1), 128–143.
5. Aiduang, W., Kumla, J., Srinuanpan, S., Thamjaree, W., Lumyong, S., & Suwannarach, N. (2022). Mechanical, physical, and chemical properties of mycelium-based composites produced from various lignocellulosic residues and fungal species. *Journal of Fungi*, 8(11), 1125. <https://doi.org/10.3390/jof8111125>
6. Zhang, M., Zhao, X., Bai, M., Xue, J., Liu, R., Huang, Y., Wang, M., & Cao, J. (2024). High-performance engineered composites biofabrication using fungi. *Small*, 20(25), e2309171. <https://doi.org/10.1002/sml.202309171>
7. Aiduang, W., Jatuwong, K., Luangharn, T., Jinanukul, P., Thamjaree, W., Teeraphantuvat, T., Waroonkun, T., & Lumyong, S. (2024). A review delving into the factors influencing mycelium-based green composites (MBCs) production and their properties for long-term sustainability targets. *Biomimetics*, 9(6), 337. <https://doi.org/10.3390/biomimetics9060337>
8. Aguirre-Pranzoni, C., Suárez, A., Kolodziej, Y., García, M. G., & Ochoa, N. A. (2026). Hyphal architecture within the trimitic system governs performance of mycelium-bound composites. *Materialia*, 48, 102769. <https://doi.org/10.1016/j.mtla.2026.102769>